



成都英维玻璃纤维有限公司

CHENGDU YINGWEI FIBERGLASS CO., LTD

REINFORCED SCRIM 5*5MM NON-WOVEN SCRIM

REINFORCED SCRIM

Scrims can be produced with a square shape pattern (orthogonal) or diamond shape pattern (triaxial). The construction can be varied from 0.4 ends per cm to 4 ends per cm. The volume and width of products available from the laid scrim process gives a security of supply with a short lead time to satisfy the most demanding customers requirements.

APPLICATION REINFORCED SCRIM

With experience of polyester, nylon and glass yarns from 76dTex to 12,000dTex in laid scrim manufacture in fabric densities from 0.4 to 4 ends per centimetre, CTC have the scrim processes to solve your reinforcement problem.

Laid scrims are used in roofing, flooring, tapes, automotive, aerospace, composites, hygiene, medical, packaging and many other industries.

REINFORCED SCRIM PICTURES



PRODUCT DATA

CONSTRUCTION	5.0*5.0mm
WARP YARN	34 TEX Glass fiber
WEFT YARN	34 TEX Glass fiber
WARP TENSILE	200N/50mm
WEFT TENSILE	200N/50mm
WARP ELONGATION	2.9 %
WEFT ELONGATION	2.9 %
MATERIAL WEIGHT:/m2±8%	15.5 g/m2
BINDER CLASS	PVOH
Bobbin(N.W.)KG	3.2-3.5
APPLICATION	Material Composite

This data is offered solely as a guide for our customers and implied no liability on our part. The information contained in this data sheet is based on actual data supplied by an independent laboratory. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any liability arising out of its use or performance. The user, by accepting these products, agrees to conduct its own testing and suitability for a particular use.

